



HSP HOT SPLICE STEEL CORD PRIMER



Photo shows 1 quart.

HSP Hot Splice Steel Cord Primer is a one-part coating for non-rubberized cords that enhance adhesions in hot vulcanized steel cord belt splicing. It is designed for use as a reactive bonding agent between metal surfaces and uncured splice materials.

FEATURES

- Can be applied directly to any exposed metal surface to increase adhesions
- Excellent brushable consistency for ease of application onto cords
- For Natural Rubber (NR), Polyisoprene (IR), Styrene-Butadiene (SBR), Polybutadiene (BR), Polychloroprene i.e. - Neoprene (CR) rubber belt splices
- Toluene Free

HSP HOT SPLICE STEEL CORD PRIMER

PRODUCT CODE	VOLUME		WEIGHT	
	L	GAL	KG	LBS
AA-HSPF-Q	.95	.25	.95	2.09

HSP PROPERTIES	
Colour	Black
Base	Mix of polymers
Solids (wt.)	20 - 25%
Formula	Xylene
Calculated Coverage	144 sf / gal / mil
Flash Point	26 °C / 79 °F (Closed Cup)
Shelf Life	6 months at 21 °C / 70 °F or 12 months at 10 °C / 50 °F



Note: The above data is based on extensive testing and represents standard values. Shaw Almex Industries reserves the right to make changes without prior notice and refuses all claims arising from such changes. All items are subject to change without previous notice.