



FABRIC BELT COVER STOCK



Fabric Belt Cover Stock is an uncured rubber used in hot vulcanized belt step and finger splicing. It is designed for use as a cover rubber replacement material when splicing fabric conveyor belts. A high abrasion compound, it will bond to cured cover rubber in all standard grades of fabric conveyor belts.

FEATURES

- Enhances working life of fabric splices
- Improves wear and tear resistance on conveyor belt splices
- Eliminates surface contamination (normal application) with double sided poly
- Uses poly color coding system to ID compound
- For Natural Rubber (NR), Polyisoprene (IR), Styrene-Butadiene (SBR), Polybutadiene (BR), Polychloroprene i.e. - Neoprene (CR) rubber belt splices

FABRIC BELT COVER STOCK

PRODUCT CODE	POLY COLOR BOTH SIDES	THICKNESS/GAUGE			WIDTH		LENGTH		ROLL WEIGHT	
		FRAC	MM	IN	M	IN	M	FT	KG	LB
AA-FBC-031	White	1/32	.7	.031	.5	20	15	49	7	15.3
AA-FBC-062	White	1/16	1.6	.063	.5	20	15	49	13.9	30.6
AA-FBC-093	White	3/32	2.3	.090	.5	20	10	33	13.3	29.3
AA-FBC-125	White	1/8	3.2	.126	.5	20	8	26	14.8	32.7
AA-FBC-156	White	5/32	3.9	.153	.5	20	8	26	18.1	39.8
AA-FBC-187	White	3/16	4.7	.185	.5	20	5	16	13.6	30
AA-FBC-218	White	7/32	5.5	.216	.5	20	5	16	16	35.1
AA-FBC-250	White	1/4	6.3	.248	.5	20	5	16	18.3	40.2

FABRIC BELT COVER STOCK PROPERTIES	
Base Polymer	NR Rubber
Rubber Color	Black
Poly Liner Color	White (double sided)
Specific Gravity	1.15 - 1.21
Hardness	65 - 75 Shore A
Rubber Tensile	2500 - 3000 psi
Rubber Elongation	300 - 500% (at break)
Shelf Life	6 Months at 70 °F (21 °C) or 12 Months at 50 °F (10 °C)



Note: The above data is based on extensive testing and represents standard values. Shaw Almex Industries reserves the right to make changes without prior notice and refuses all claims arising from such changes. All items are subject to change without previous notice.